



TECHNICKÝ LIST - Safety Base Sealbar Super
DoP Nr 1161188801000



1. Samolepiaci pás na skladbu striech
2. Zloženie: nosič zo sklených vlákien, SBS modifikovaná hydroizolačná asfaltová hmota, protišmyková popieskovaná vrchná vrstva, spodná strana samolepiaca, potiahnutá ľahko snímateľnou fóliou
3. **Aplikácia:** samolepiaci pás, nutné mechanické kotvenie. Na šikmé strechy, kde je sklon > 20 °, teplota spracovania 5 °C.
4. **Skladovanie:** vo vnútri skladu, balené na paletu vertikálne, uchovávať zvisle mimo dosah zdrojov tepla.
5. Materiál neobsahuje azbest, zlúčeniny dechtu ani iné nebezpečné látky.
6. Technický list môže výrobca aktualizovať bez predchádzajúceho upozornenia.

Asfaltová zmes		SBS modifikovaný
Dĺžka / šírka	EN 1848-1	15 m x 1m (± 1 %)
Priamosť		< 20 mm/10m
Hmotnosť	EN 1849-1	1,8 kg/m ² (± 10 %)
Chemické a fyzikálne vlastnosti		
Viditeľné chyby	EN 1850-1	vizuálne žiadne
Predĺženie MD/CMD	EN 12311-1	35/35 % (-15)
Pevnosť v ťahu MD/CMD	EN 12311-1	450/300 N/5cm (± 20 %)
Odolnosť proti pretrhnutiu klincom	EN 12310-1	>80 / >80 N
Odolnosť voči prieniku vody	EN 1928	W1
Rozmerová stabilita MD/CMD (m.A)	EN 1107-1	%
Flexibilita pri nízkych teplotách	EN 1109	< -20 °C
Prenos vodnej pary	EN 1931	NPD p
Pevnosť v ťahu MD/CMD v umelo vytvorenom prostredí starnutia a pri vysokých teplotách	EN 13859-1 metóda C	350/200 N/5cm (± 20 %)
Predĺženie MD/CMD v umelo vytvorenom prostredí starnutia a pri vysokých teplotách	EN 13859-1 metóda C	25/25 % (-15)
Vodeodolnosť v umelo vytvorenom prostredí starnutia	EN 13859-1 metóda C	W1
Pôsobenie požiaru		
Odolnosť pôsobenie vonkajšieho požiaru	EN 13501-5	F Roof
Reakcia na oheň	EN 13501-1	trieda F
Balenie		
Typ	papier	
Balenie paleta	30ks/450 m ²	

Tegola Bohemia, s.r.o.
an IWIS group company
Březecká 795/12
193 00 Praha 9 - Počernice

IČ: 15887391
DIČ: CZ15887391

www.tegola.cz
tegola@tegola.cz
tel.: +420 286 882 946



Rev.04 - 14/09/19
1161188801000

Description:	Self-adhesive underlayer for discontinuous roofing.
Composition:	Carrier in fiberglass; SBS modified waterproofing bitumen mass; antiasherent upper layer made of sand; self-adhesive lower layer, covered with removable film.
Application:	Self-adhesive product. Mechanical fastening required. Application on pitched roof, where slope >20°. Application temperature >+10°C.

DIMENSIONS

				tol.
Lenght	EN 1848-1	m	15	+ 1 %
Width	EN 1848-1	m	1	+ 1 %
Weight per Unit Area	EN 1849-1	kg/m ²	1,8	± 10 %
Straightness	EN 1848-1	mm/10m	<20	-

CHEMICAL AND PHYSICAL PROPERTIES

				tol.
Visible Defects	EN 1850-1	Visual	None	-
Tensile Resistance MD/CMD	EN 12311-1	N/5cm	450 / 300	± 20 %
Elongation MD/CMD	EN 12311-1	%	35 / 35	- 15
Resistance to Tearing (Nail Method)	EN 12310-1	N	>80 / >80	
Resistance to water penetration	EN 1928	Class	W1	
Flexibility at low temperature	EN 1109	°C	<-20	
Dimensional Stability MD/CMD (Method A)	EN 1107-1	%	-	
Water Vapour Transmission	EN 1931	μ	NPD	
Tensile strength, after artificial ageing by long term exposure to elevated temperature MD/CMD	EN 13859-1 Annex C	N/5cm	350 / 200	± 20 %
Elongation, after artificial ageing by long term exposure to elevated temperature MD/CMD	EN 13859-1 Annex C	%	25 / 25	- 15
Durability of resistance to water penetration, after artificial ageing	EN 13859-1 Annex C	Class	W1	-

NPD: No Performance Determined

FIRE BEHAVIOR

External Fire Resistance	EN 13501-5	Class	F Roof
Reaction to Fire	EN 13501-1	Class	F

PACKAGING

Type	Paper
Rolls/Pallet	30
m ² /pallet	450

PRODUCT DESTINATION (according EN13859-1)

Underlayer for discontinuous roofing.

Safety:	Material is asbestos, tar compounds and dangerous substances free.
Storage:	Material is packed vertically on pallet. Keep vertically and in warehouse. Keep away from heat sources.
Other:	The producer can update the tds without notice.

TEGOLA

Tegola Canadese Srl, via dell'Industria 21 31029 Vittorio V.to Italy
www.tegolacanadese.com

