



TECHNICKÝ LIST - Safety Base 2 Overlap

DoP Nr 1152208801000



1. Asfaltová membrána na hydroizoláciu striech.
2. Materiál neobsahuje azbest, zlúčeniny dechtu ani iné nebezpečné látky.
3. Zloženie: nosič zo sklenených vlákien, hydroizolačná bitúmenová hmota upravená APP, vrchná a spodná vrstva popieskovaná, samolepiaci bočný pás na prekrytie.
4. Aplikácia: mechanickým kotvením, teplota > 5°C.
5. Skladovanie: vo vnútri skladu, palety nestohovať na seba, balené na paletu vertikálne, uchovávať mimo dosah zdrojov tepla.
6. Technický list môže výrobca aktualizovať bez predchádzajúceho upozornenia.

Asfaltová zmes		APP modifikovaný
Dĺžka	EN 1848-1	15 m (± 1 %)
Šírka		1 m (± 1 %)
Priamosť	EN 1848-1	<30 mm/10m
Chemické a fyzikálne vlastnosti		
Hmotnosť	EN 1849-1	2,2 kg/m ² (± 10 %)
Viditeľné chyby	EN 1850-1	vizuálne žiadne
Predĺženie MD/CMD	EN 12311-1	>2/>2 %
Pevnosť v ťahu MD/CMD	EN 12311-1	>450/300 N/5cm (± 20 %)
Odolnosť proti pretrhnutiu klincom	EN 12310-1	>60/>60 N
Odolnosť voči prieniku vody	EN 1928	W1
Odolnosť voči nízkym teplotám	EN 1109	<-15° C
Rozmerová stabilita MD/CMD (metóda A)	EN 1107-1	%
Prenos vodnej pary	EN 1931	NPD/μ
Pevnosť v ťahu / umelo vytvorené prostredie dlhodobu zvýšenej teploty	EN 13859-1 metóda C	350/200 N/5cm (± 20 %)
Predĺženie v ťahu / umelo vytvorené prostredie dlhodobu zvýšenej teploty	EN 13859-1 metóda C	> 1/>1 %
Odolnosť voči prieniku vody / umelo vytvorené prostredie starnutia	EN 13859-1 metóda C	W1
Pôsobenie požiaru		
Odolnosť voči pôsobení vonkajšieho požiaru	EN 13501-5	F Roof
Reakcia na oheň	EN 13501-1	trieda F
Balenie		
Typ		lepiaca páska
Balenie paleta		30ks/450 m ²

Rev.18 – 14 /09/19 1152208801000

Tegola Bohemia, s.r.o.
an IWIS group company
Březecká 795/12
193 00 Praha 9 - Počernice

tel.: +420 602 259 899
IČ: 15887391 DIČ:
CZ15887391

www.tegola.cz
tegola@tegola.cz



Safety BASE 2 Overlap



DoP Nr
1152208801000

Description: Underlayer for discontinuous roofing.
Composition: Carrier in fiberglass; waterproofing APP modified bitumen mass; antiadherent upper and lower side made of sand. Self-adhesive side selvedge for overlapping.
Application: Mechanical fastening required. Application on roofs. Application temperature >5°C.

DIMENSIONS

				tol.
Length	EN 1848-1	m	15	+ 1 %
Width	EN 1848-1	m	1	+ 1 %
Weight per Unit Area	EN 1849-1	kg/m ²	2,2	± 10 %
Straightness	EN 1848-1	mm/10m	<30	-

CHEMICAL AND PHYSICAL PROPERTIES

				tol.
Visible Defects	EN 1850-1	Visual	None	-
Tensile Resistance MD/CMD	EN 12311-1	N/5cm	450 / 300	± 20 %
Elongation MD/CMD	EN 12311-1	%	>2 / >2	-
Resistance to Tearing (Nail Method)	EN 12310-1	N	>60 / >60	-
Resistance to water penetration	EN 1928	Class	W1	0
Flexibility at low temperature	EN 1109	°C	<-15	0
Dimensional Stability MD/CMD (Method A)	EN 1107-1	%	-	-
Water Vapour Transmission	EN 1931	μ	NPD	-
Tensile strength, after artificial ageing by long term exposure to elevated temperature MD/CMD	EN 13859-1	N/5cm	350 / 200	± 20 %
Elongation, after artificial ageing by long term exposure to elevated temperature MD/CMD	EN 13859-1	%	>1 / >1	-
Durability of resistance to water penetration, after artificial ageing	EN 13859-1 Annex C	Class	W1-	-

NPD: No Performance Determined

FIRE BEHAVIOR

External Fire Resistance	EN 13501-5	Class	F Roof
Reaction to Fire	EN 13501-1	Class	F

PACKAGING

Type	Adhesive Tape
Rolls/Pallet	30
m ² /pallet	450

PRODUCT DESTINATION (according EN 13859-1)

Underlayer for discontinuous roofing.

Safety: Material is asbestos, tar compounds and dangerous substances free.
Storage: Material is packed vertically on pallet. Keep vertically and in warehouse. Keep away from heat sources.
Other: The producer can update the tds without notice.

TEGOLA

Tegola Canadese SpA, via dell'Industria 21 31029 Vittorio V.to Italy
www.tegolacanadese.com



Rev.18 – 14 /09/19 1152208801000